

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 59-027976

(43)Date of publication of application : 14.02.1984

(51)Int.Cl. C09J 3/16
C08K 3/22
C08L 63/00

(21)Application number : 57-137811

(71)Applicant : SUNSTAR GIKEN KK

(22)Date of filing : 06.08.1982

(72)Inventor : SAKAKIBARA TOSHIMORI

(54) STRUCTURAL ADHESIVE COMPOSITION

(57)Abstract:

PURPOSE: To provide the titled adhesive compsn. excellent in rust prevention, capable of electrodeposition coating, well suited for use in assembly of automobile bodies, etc., by mixing epoxy resins, heat-active hardeners, and metallic oxide-iron oxide sintered complex ferrite or α -Fe₂O₃ powder.

CONSTITUTION: 100pts.wt. epoxy resin (e.g., glycidyl ether-type epoxy resin), about 1W15pts.wt. heat-active hardener (e.g., dicyandiamide, 4,4'-diaminodiphenyl sulfone), and about 20W150pts.wt. metallic oxide-iron oxide sintered complex ferrite of formula MeO.Fe₂O₃ (wherein Me is a divalent metal) (e.g., BaO.Fe₂O₃) or α -Fe₂O₃ powder are mixed to yield the intended structural adhesive compsn. Metallic oxide-iron oxide sintered complex is yielded by mixing metallic oxides (e.g., MnO, BaCO₃) with iron oxide powder, sintering and then pulverizing.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office